

SYSTEM CHART

ROCKCOTE RENDER SYSTEM for Acrylic Renders over Pre-painted Surfaces

Surface Preparation

Remove all deleterious and loose materials and leave surfaces clean and free of dust, oil, dirt, mould or any other contamination. Clean down surface removing all dirt, grease, oil, silicone, mould & fungi. Check the adhesion of the existing paint on every wall and at least every 3 metres over the proposed application areas.

Any loose or peeling paint should be scraped back to a firm & sound substrate. Apply an alkali-resistant, penetrating primer /sealer if the old paint is oxidized or chalky.

Glossy and smooth surfaces should be sanded with a coarse grit sanding paper to ensure a key for satisfactory adhesion.

Patch deep holes or deviations with ROCKCOTE Hard Patch & let cure. Optional coat of ROCKCOTE Texprime may be applied and allowed to dry for a minimum period of 4 hours prior to subsequent coats.

Colour

Only colours with a Light Reflectance Value (LRV) of 25% or higher are suitable for use over insulation board systems.

Only colours with a LRV of 40% or higher are suitable for use over fibre cement sheeting.

Please refer to the relevant Technical Specification & Material Safety Data Sheet before application.

PERFORMANCE CODE 5

Finish	1st Step	2nd Step	3rd Step	4th Step
Finecote	Reno Render	1mm Finecote *	Armour Plus	Armour Plus
Quicksand	Reno Render	Quicksand	Armour Plus	Armour Plus
Sandcote	Reno Render	Sandcote	Armour Plus	Armour Plus
Santa Fe	Reno Render	Santa Fe	Armour Plus	Armour Plus
Santini	Reno Render	1mm Santini *	Armour Plus	Armour Plus
Sponge Finish	Reno Render	Polymer Render	Armour Plus	Armour Plus
Trowel-On	Reno Render	Trowel-On	Armour Plus	Armour Plus

* ROCKCOTE Finecote and Santini may require two applications to achieve 1mm dry film build

PERFORMANCE CODE 4

Finish	1st Step	2nd Step	3rd Step	4th Step
Armour Flex (Low Profile)	Reno Render	Armour Flex, (stipple)	Armour Flex	n/a
Concote (Medium Profile)	Reno Render	Concote (medium texture roller)	Armour Plus	Armour Plus

SYSTEM CHART

PERFORMANCE CODE 3

Finish	1st Step	2nd Step	3rd Step	4th Step
Finecote	Reno Render	1mm Finecote *	Armour Flex	n/a
Quicksand	Reno Render	Quicksand	Armour Flex	n/a
Sandcote	Reno Render	Sandcote	Armour Flex	n/a
Santa Fe	Reno Render	Santa Fe	Armour Flex	n/a
Santini	Reno Render	1mm Santini *	Armour Flex	n/a
Sponge Finish	Reno Render	Polymer Render	Armour Flex	n/a
Trowel-On	Reno Render	Trowel-On	Armour Flex	n/a

* ROCKCOTE Finecote and Santini may require two applications to achieve 1mm dry film build

PERFORMANCE CODE 2

Finish	1st Step	2nd Step	3rd Step	4th Step**
Finecote	Reno Render	Tinted Primer	1mm Finecote *	ROCKCOTE Repel or Clearcote
Quicksand	Reno Render	Tinted Primer	Quicksand	ROCKCOTE Repel or Clearcote
Sandcote	Reno Render	Tinted Primer	Sandcote	ROCKCOTE Repel or Clearcote
Santa Fe	Reno Render	Tinted Primer	Santa Fe	ROCKCOTE Repel or Clearcote
Santini	Reno Render	Tinted Primer	1mm Santini *	ROCKCOTE Repel or Clearcote
Trowel-On	Reno Render	Tinted Primer	Armour Plus	ROCKCOTE Repel or Clearcote

* ROCKCOTE Finecote and Santini may require two applications to achieve 1mm dry film build

** This step is optional. For extra durability, the application of ROCKCOTE Clearcote or ROCKCOTE Repel is recommended. ROCKCOTE Clearcote provides a satin finish, whilst ROCKCOTE Repel provides a natural look.

PERFORMANCE CODE 1

Finish	1st Step	2nd Step	3rd Step	4th Step
Concote	Reno Render	Polymer Render	Tinted Primer	Concote
Render Paint Fine	Reno Render	Polymer Render	Render Paint Fine	Render Paint Fine
Render Paint Flat	Reno Render	Polymer Render	Render Paint Flat	Render Paint Flat
Santini	Reno Render	Polymer Render	Tinted Primer	1mm Santini *
Torino	Reno Render	Polymer Render	Torino	Torino
Toscani	Reno Render	Polymer Render	Toscani	Toscani

* ROCKCOTE Finecote and Santini may require two applications to achieve 1mm dry film build

Indemnity

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice.