

TECHNICAL SPECIFICATION

ROCKCOTE PROTECTIVE STYLING TEXTURE

Last Updated: Dec 2011
 Technical Specification: Version 2

Description Rockcote Protective Styling Texture is a high performance flexible acrylic texture coating manufactured using 100% acrylic emulsions and other additives blended together to provide long term protection and decoration over masonry substrates.

Features

Water based
 Excellent flexibility
 Vapour permeable
 Easy to maintain
 Can be applied with roller or trowel.

Benefits

Can be tinted to a range of colours
 Long term exterior durability
 Mould resistant
 High crack bridging capabilities

Uses

- Rockcote Protective Styling Texture is suitable to go over properly prepared substrates such as, cement render, Rockcote renders and textures, concrete, cement sheeting, AAC panels/blocks. For bricks and block, use Rockcote MutiBlend Masonry Render as a basecoat to flush the mortar joints. Refer to Technical specification for MutiBlend Masonry Render).
- Can achieve a medium sized texture.
- Can be used interior and exterior.

Colours

- Can be tinted to a wide range of colours.

Typical Data

Coverage Rate: 1 m ² /litre	Volume Solids: 70%
Wet Film Build: 1 - 1.2 mm	Dry Film Build: 1 - 1.2mm
Touch Dry: 5hrs	Dry to Recoat: 24hrs
Full Curing Time: 2 weeks	Water Resistance: Good
Thinning: Up to 5% water.	
Clean Up: Water.	

Substrate Conditions

- Rockcote Protective Styling Texture must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- All substrates must not contain no more than 15% moisture prior to application.
- Do not apply Rockcote Protective Styling Texture if air and surface temperatures are below 10°C or above 35°C.
- Rockcote Protective Styling Texture must be applied over flat substrate with flushed joints. (Refer to Rockcote website for preparing joints).
- If applying over Rockcote Multiblend Masonry Render, application of Rockcote Protective Styling Texture may proceed after 48hrs if properly cured and provided the moisture content is no more than 15% WME.

TECHNICAL SPECIFICATION

ROCKCOTE Protective Styling Texture

Application

- If using multiple pails of tinted Rockcote Protective Styling Texture on the same wall, then ensure all pails have been tinted to the same colour prior to application.
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions.
- If joining up to previous day's application, mask up to the previous days' work to give a clean join line.
- Keep the finished Rockcote Protective Styling Texture sheltered from rain & moisture for 24 -48 hours after completion dependent on climatic conditions.
- Can be applied with high profile texture roller, spray or steel trowel and finish with plastic float.

Safety Data

- Refer to MSDS.

Precautions and Limitations

- Rockcote Protective Styling Texture should not be applied in temperatures below 10°C or above 35°C.
- If applying over site-mixed sand and cement mixture, allow 28 days for proper curing before applying Rockcote Protective Styling Texture.
- Do not apply if rain is imminent.
- Rockcote Protective Styling Texture is not suitable for areas of continual damp or areas that can be submerged in water.
- Rockcote Protective Styling Texture is not suitable for floors.

Transport and Storage

- Storage Life is up to 24 months if kept in cool dry conditions.
- Keep pail sealed.
- Do not stack over 4 high.

Disclaimer

RockcoteEnterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice.

ROCKCOTE ENTERPRISES PTY LTD

ABN 42 066 227 174

HEAD OFFICE

18 Machinery Rd, Yandina Q 4561

PO Box 230, Yandina Q 4561

Ph: 07 5446 7737

E: sales@rockcote.com.au

1 300 736 668

WWW.ROCKCOTE.COM.AU