

Page 1 of 2 Updated July 2009

ROCKCOTE Quicksand is a ready mixed, pre-coloured acrylic coating ideal for covering and decorating suitably prepared interior or exterior surfaces such as concrete, concrete blocks, cement render, Hebel A.A.C., fibre cement sheeting, brickwork, expanded polystyrene, plasterboard and most common building substrates when properly prepared

ROCKCOTE Quicksand effectively imparts a seam-free, solid-rendered effect and natural ambiance to drab concrete walls with the performance properties of modern flexible 100% acrylic polymer protection.

### PERFORMANCE & PROPERTIES

---

#### Adhesion

ROCKCOTE Quicksand exhibits excellent adhesion to all common building materials if correct surface preparation is carried out in accordance with ROCKCOTE Specifications.

#### Durability

ROCKCOTE Quicksand is knock resistant, scuff resistant and can resist extremes of weather and attack from fungi and mould. For exterior use, where a higher level of water resistance, dirt/mould pick up resistance and durability is required, ROCKCOTE Quicksand should be over-coated with ROCKCOTE's Armour range, Clearcote or EcoStyle Low Sheen (refer to the ROCKCOTE Render System - Performance Codes for more information.) Before over-coating ROCKCOTE Quicksand with a paint coating, refer to the ROCKCOTE Technical Article for 'Cutting in and Avoiding Picture Framing.'

ROCKCOTE Quicksand provides a flexible finish that is resistant to micro-cracking caused by thermal expansion and contraction of the substrate. It also remains vapour permeable, allowing the walls to "breathe".

#### Colours Available

ROCKCOTE Quicksand can be tinted to a wide range of colours from soft, natural tones to vibrant colours. Light-fastness of chosen exterior colours must be confirmed before ordering. Durability of the tinted ROCKCOTE Quicksand can be improved by over-coating with ROCKCOTE Clearcote.

ROCKCOTE Quicksand provides a natural sand finish including aggregate particles of varying natural colour. If this effect is not the desired effect, then over-coat with two coats of ROCKCOTE Armour Plus.

#### Limitations

Application should not be carried out in temperatures below 5°C or above 35°C or in strong winds. As ROCKCOTE Quicksand is manufactured from natural, mineral sands some variation in colour may occur from batch to batch. It is recommended that material be ordered in job lots. Material from later batches should be restricted to separate areas where colour differences will not be noticed.

ROCKCOTE Quicksand is not suitable for areas subject to total immersion in water, areas where water ponding may occur or for use on roof tops.

### SURFACE PREPARATION

---

All surfaces should be clean and free from loose material such as drummy sections and flaking paint. Powdery surfaces should not be coated with ROCKCOTE Quicksand. Glossy surfaces should be lightly sanded and washed clean before priming. Dirty surfaces should be washed down with warm water mixed with biodegradable detergent and flushed with clean water. Mould should be removed by cleaning and surfaces treated with a proprietary surface sanitiser with residual action. Fill cracks and other surface imperfections with suitable ROCKCOTE patching compounds.

Only dry surfaces should be coated and substrates must contain less than 15% WME (Wood-Moisture-Equivalent) before painting. ROCKCOTE cement based renders can be coated 48 hours after dry. Other new cement based surfaces should not be coated until 30 days old.

### APPLICATION

---

#### Concrete Block and Brick Walls *(Where mortar joints and other imperfections need to be concealed)*

ROCKCOTE Quick Render or ROCKCOTE QRender Thin Section should be applied according to specifications and left as a float finish.

A coat of ROCKCOTE Texprime applied to the render is recommended where the ROCKCOTE Quicksand will be tinted and not over-painted with an opaque top-coat. The primer should be tinted to a similar colour. If ROCKCOTE render has been used and if the Quicksand will be over-painted with an opaque top-coat, priming of the render is not necessary.

ROCKCOTE Quicksand is applied by steel trowel then finished with a plastic or polyurethane float.

A wet edge should be maintained throughout the application and day joints formed at corners, expansion joints or mouldings where they will not be evident in the finish. Finished work must be protected from inclement weather conditions for 48 hours after application and protected from damage until the completion of the project.

**Smooth Surfaces** (*Previously rendered masonry, concrete or cement sheeting*)

Apply one coat of ROCKCOTE Texprime followed by one coat of ROCKCOTE Quicksand as described above.

To obtain a more even finish on uneven masonry surfaces, the primer coat should be replaced by one trowelled coat of ROCKCOTE Polymer Render. Where the ROCKCOTE Quicksand will be tinted and not over-painted with an opaque top-coat, it is recommended to prime the Polymer Render first using ROCKCOTE Texprime, tinted to a similar colour.

The application of ROCKCOTE Quicksand is a specialist procedure and should only be carried out by a skilled & experienced applicator and in accordance with ROCKCOTE Technical Specifications.

|   |  |
|---|--|
| Thinning                                | ROCKCOTE Quicksand usually does not require thinning but may be thinned up to 5% by volume with clean water if required. |
| Clean Up                                | Clean with water immediately after use. Recently dried material can be removed with methylated spirits.                  |
| Flammability                            | Non Flammable  |
| Drying<br>(55% Relative Humidity, 25°C) | Touch dry in 5 hours. Dry to recoat in 48 hours. (Dry times vary with changes in temperature and humidity).              |
| Pack Size                               | 15L plastic pails.   |
| Finish                                  | Low sheen and highly textured.   |
| Maintenance                             | Any identified damaged should be repaired as soon as possible. Refer to ROCKCOTE specification on General Maintenance.   |
| Durability                              | Excellent interior or exterior. See ROCKCOTE Render System - Performance Codes   |

## THEORETICAL COVERAGE RATES

Theoretical coverage per coat is 0.8 - 1.0 m<sup>2</sup> /L (12 to 15 m<sup>2</sup> per 15L pail).

Figures are a guide only. Coverage rates vary according to application technique and substrate preparation.

## STORAGE, SAFETY & HANDLING

### Refer to the MSDS for ROCKCOTE Quicksand

Pails should not be stacked more than three high during transportation and should be stored out of direct sunlight and above 4°C.

When working with ROCKCOTE Quicksand, observe the usual precautions for handling water borne acrylic based products.

Avoid inhalation of vapour, prolonged skin contact and particularly eye contact.

If skin or eye contact occurs, flush thoroughly with clean water and see a doctor if irritation occurs.

If ingestion occurs, drink at least two glasses of water and consult a doctor.

Wear protective clothing to minimise skin contact, and wear goggles where spatter is likely

In an emergency contact Poisons Information Ph: 13 11 26

## PROPER DISPOSAL OF EXCESS AND WASTE PRODUCT

Spilt material must be absorbed with sand/sawdust and lifted for proper disposal. Spilled product must not be allowed to run into drains or open bodies of water. Residual small amounts of leftover paint on brushes and rollers should be wiped on to old newspaper and allowed to dry, rather than being washed down the sink. Dispose in accordance with Local Council regulations.

ROCKCOTE Quicksand is suitable for disposal through the RA Industries Reclaimer Portable Paint Wash Recycling System.

### Indemnity

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled & experienced applicator.  
WWW.ROCKCOTE.COM.AU