

ROCKCOTE Render Paint Fine is a flat finish acrylic coating suitable for use over suitably prepared surfaces such as brickwork, concrete, cement render, Hebel A.A.C. A 100% acrylic coating, ROCKCOTE Render Paint Fine can be applied as a final finish over ROCKCOTE render coatings for added durability, but primarily to decorate and minimise the appearance of surface imperfections with an attractive, flat, sponge finish look.

PERFORMANCE & PROPERTIES

Adhesion

ROCKCOTE Render Paint Fine adheres well to most common masonry building materials if correct surface preparation is carried out in accordance with ROCKCOTE specifications.

Colours Available

ROCKCOTE Render Paint Fine can be tinted to a wide range of colours from soft natural tones to deep or bright colours. Light-fastness of chosen exterior colours must be confirmed before ordering.

Limitations

- ROCKCOTE Render Paint Fine is not recommended for floors, and is not suitable for areas that will be totally submerged in water or subjected to continual moisture.
- ROCKCOTE Render Paint Fine is not recommended for use over dimensionally unstable substrates such as poor quality site mixed render.
- ROCKCOTE Render Paint Fine is not suitable for high wear areas such as handrails, outdoor furniture or roofs.
- ROCKCOTE Render Paint Fine is unsuitable for use on exterior timber.
- Flat paints tend to pick up more dirt than low sheen or glossy surfaces and it is important to clean the exterior surfaces painted with ROCKCOTE Render Paint Fine regularly. See ROCKCOTE data sheet on General Maintenance.

SURFACE PREPARATION

All surfaces should be clean and free from loose material such as drummy sections and flaking paint. Powdery surfaces should not be painted with ROCKCOTE Render Paint Fine.

Glossy surfaces should be lightly sanded and washed clean.

Wash down dirty surfaces with warm water mixed with detergent then flush with clean water.

Remove mould and mildew by cleaning with a proprietary mould remover and then treat with a proprietary pre-painting surface sanitiser with residual action. Fill cracks and other surface imperfections with suitable Rockcote patching compounds.

Substrates must contain less than 15% Wood-Moisture-Equivalent (%WME) before painting.

ROCKCOTE cement based renders can be coated 48 hours after drying. Other new cementitious surfaces should not be coated until 30 days old.

APPLICATION

ROCKCOTE Render Paint Fine is applied by brush, roller or spray. A minimum of two coats should be applied, allowing at least 4 hours drying time between coats. Application should not be carried out in temperatures below 5°C or above 35°C or in strong winds.

Thinning	Do not thin ROCKCOTE Render Paint Fine.
Flammability	Non Flammable
Clean Up	Clean with water immediately after use. Recently dried material can be removed with methylated spirits.
Volume Solids	47%
Drying (55% Relative Humidity, 25°C)	Touch dry in 1.5 hours. Dry to recoat in 4 hours. (Dry times vary with changes in temperature and humidity)
Pack Size	15L Heavy Duty Plastic. Smaller sizes available on request
Finish	Flat and textured. Contains washed graded white sand
Maintenance	Any identified damaged should be repaired as soon as possible.
Usual number of coats	2

THEORETICAL SPREADING RATES

Description of Surface	Litres per Square Metre (L/ m ²)	Square metres per litre (m ² /L)	Square metres per 15 Litre Pail
Concrete, Cement Render & Cement Sheeting (primed)	0.20	5.0	75

SPREADING RATES above are APPROXIMATE ONLY and may vary according to substrate, preparation, wastage factors and application techniques.

STORAGE, SAFETY & HANDLING

Refer to the ROCKCOTE MSDS for Render Paint Fine

- Pails should not be stacked more than three high during transportation and should be stored out of direct sunlight and above 4°C.
- When working with ROCKCOTE Render Paint Fine, observe the usual precautions for handling water-borne acrylic based products.
- Avoid inhalation of vapour, prolonged skin contact and particularly eye contact.
- If skin or eye contact occurs, flush thoroughly with clean water and see a doctor if irritation occurs.
- If ingestion occurs, drink at least 2 glasses of water and consult a doctor.
- Wear protective clothing to minimise skin contact, and wear goggles where spatter is likely.
- In emergency contact Poisons Information PH:13 11 26

PROPER DISPOSAL OF EXCESS & WASTE PRODUCT

- Spilt material must be absorbed with sand/sawdust and lifted for proper disposal. Spilled product must not be allowed to run into drains or open bodies of water. Residual small amounts of leftover paint on brushes and rollers should be wiped on to old newspaper and allowed to dry, rather than being washed down the sink. Dispose of in accordance with local council regulations.
- ROCKCOTE Render Paint Fine is suitable for disposal through the RA Industries Reclaimer Portable Paint Wash Recycling System.

Indemnity

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice.