

Technical Data Sheet

ROCKCOTE CERANO

Effective From 08 Dec, 2018

ROCKCOTE Cerano is a flexible acrylic based coating manufactured using 100% acrylic emulsions, quality graded quartz and other additives blended together to provide a smooth concrete look finish over many substrates. ROCKCOTE Cerano provides a seamless and natural solid rendered look, with the flexibility and performance required for all solid masonry substrates and modern lightweight walling systems.

Features

- Water based
- Ease of use
- Vapour permeable

Benefits

- Tough
- Flexible
- Water resistant
- Excellent adhesion
- Long term exterior protection

Uses

- ROCKCOTE Cerano is suitable for application over properly prepared substrates such as brick, block, cement render, ROCKCOTE Render, concrete, cement sheeting, A.A.C panels/blocks and plasterboard.
- Can be used interior and exterior.

Colours and Gloss

- Can be tinted to a wide range of colours achieving a natural finish.
- Low Sheen when over coated with ROCKCOTE Repel.

Sheen Level

Coverage Rate

2 - 2.5 m² per 1 litre

Coverage rates may vary according to substrate and preparation. ROCKCOTE Cerano is usually applied at a rate of 2 - 2.5 square metres per 1 litre.

Application Method

Hawk and trowel

Dry Film Build

Approximately 0.25mm per coat

Wet Film Build

Typical Data at 25°C and 50% Relative Humidity

Drying Time 24 hours

Touch Dry 2 hours

Dry to Recoat 4 hours

Usual No Coats

2

Clean Up

Water

Packaging Sizes

Trade 20L 15L 10L 4L 1L

Volume Solids

Thinning

Up to 5%

Elongation Rate

Crack Bridging

Abrasion Resistance

Excellent

Moisture Control

Water Resistance

Technical Data Sheet

ROCKCOTE CERANO

Effective From	08 Dec, 2018
-----------------------	--------------

Substrate Conditions

- ROCKCOTE Cerano must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- Substrates must not contain more than 15% WME prior to application.
- Do not apply if air and surface temperatures are below 5°C or above 35°C.
- If applying over ROCKCOTE Quick Render, application may proceed after 48 hours if properly cured.
- Fresh cementitious substrates such as site mix sand and cement render and concrete must be left for up to 28 days to sufficiently cure prior to application of ROCKCOTE Cerano.
- ROCKCOTE Anti Efflorescent primer should be used when applying over site mix render.

Application

- Check colour before use.
- Ensure same batch numbers are used on a single wall where possible.
- Apply evenly over the properly prepared substrate with a hawk and trowel
- Ideally apply slightly thicker than the granules to achieve optimum results.
- Finish with a steel or Venetian trowel.
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions.
- If joining up to previous day's application, it is "good working practice" to start and finish on an external or internal corner.
- Keep sheltered from rain & moisture for 24-48 hrs after completion dependent on climatic conditions.
- It is advisable to apply a primer that is tinted to the required finish colour before the application of ROCKCOTE Cerano.
- Over coat with 2 coats of ROCKCOTE Repel or ROCKCOTE Clearcote.

Precautions and Limitations

- Check colour before use.
- Ensure same batch numbers are used on a single wall where possible.
- Should not be applied in temperatures below 5°C or above 35°C.
- Not suitable for areas of continual damp or areas submerged in water

Transport and Storage

- Store in a cool dark place
- Keep pail sealed
- Do not stack over 3 high

Disposal

- Dispose of in accordance with local council regulations

Technical Data Sheet



ROCKCOTE CERANO

Effective From	08 Dec, 2018
-----------------------	--------------

Safety Data

Refer to ROCKCOTE Cerano SDS

Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.