

Technical Data Sheet

ROCKCOTE SANDCOTE HYDRATECH

Printed: March 21, 2018	Effective From	Effective To
Status at time of print: Active	21 Mar, 2018	

ROCKCOTE Sandcote HYDRATECH is a flexible acrylic based coating manufactured using 100% acrylic emulsions, quality graded quartz and other additives blended together to provide a natural coloured render finish over many substrates. ROCKCOTE Sandcote HYDRATECH is a new generation Sandcote with water repellency embedded into the chemical composition of the coating, delivering a hydrophobic system. ROCKCOTE Sandcote HYDRATECH is an attractive and natural coloured render that uses the inherent beauty of mineral sands and aggregates to produce a natural but stylishly modern texture finish. ROCKCOTE Sandcote HYDRATECH has been designed as a coloured render that delivers water repellency without the need to overcoat with ROCKCOTE Repel.

Features

- Water based.
- Ease of use.
- No sponge finishing required.
- Vapour permeable.

Benefits

- Tough.
- Flexible.
- Water repellent.
- Excellent adhesion.
- Long term exterior protection.
- Natural coloured render finish that does not require painting.

Uses

- ROCKCOTE Sandcote HYDRATECH is suitable to go over properly prepared substrates such as brick, block, cement render, ROCKCOTE render, concrete, cement sheeting, AAC panels/blocks, and plasterboard.
- Can be used interior and exterior.
- Can be over coated with ROCKCOTE Repel or ROCKCOTE Clearcote for added durability and low maintenance.
- ROCKCOTE Sandcote HYDRATECH has been designed as a Coloured Render, however it can be painted provided it is primed with ROCKCOTE Masonry Primer Hi Op prior to coating with 2 coats of ROCKCOTE Armour or Armour Flex.

Colours and Gloss

- Can be tinted to a wide range of colours from soft natural colours, to strong vibrant colours, while still maintaining an attractive natural appearance.

Sheen Level Matt

Coverage Rate 10/15ltr
Coverage rates may vary according to substrate and preparation. ROCKCOTE Sandcote HYDRATECH is usually applied at the rate of approximately 10 square metres per 15 litre drum.

Technical Data Sheet

ROCKCOTE SANDCOTE HYDRATECH

Printed: March 21, 2018	Effective From	Effective To
Status at time of print: Active	21 Mar, 2018	

Application Method Trowel

Dry Film Build 1mm

Wet Film Build

Typical Data at 25°C and 50% Relative Humidity

Drying Time 48 hours

Touch Dry 5 hours

Dry to Recoat 48 hours

Usual No Coats 1

Clean Up Water

Packaging Sizes Trade 20L 15L 10L 4L 1L

Volume Solids

Thinning Up to 5%

Elongation Rate

Crack Bridging Bridge cracks up to 900µm per applied coat.

Abrasion Resistance Excellent

Moisture Control

Water Resistance

Substrate Conditions

- ROCKCOTE Sandcote HYDRATECH must be applied over properly prepared substrates that are free of dirt, dust, grime and any other contaminants.
- Substrates must not contain more than 15% moisture (WME) prior to application.
- Do not apply if air and surface temperatures are below 5°C or above 35°C.
- If applying over ROCKCOTE Quick Render, application may proceed after 48 hours if properly cured.
- Fresh cementitious substrates such as site mix sand and cement render and concrete must be left for up to 28 days to sufficiently cure prior to application of ROCKCOTE Sandcote HYDRATECH.
- ROCKCOTE Anti Efflorescent Primer should be used when applying over site mix render.

Mixing Mix to help reactivate and aerate contents.

Application

- Check colour before use.
- Ensure same batch numbers are used on a single wall where possible.
- Apply evenly over the properly prepared substrate with a hawk and trowel.
- Ideally apply slightly thicker than the sand granules to achieve optimum results.
- Using circular motions finish with a plastic float/trowel.
- Be sure to keep a wet edge with this product and plan your work to suit the product and weather conditions.
- If joining up to previous day's application, it is "good working practice" to start and finish on an external or internal corner.
- Keep sheltered from rain and moisture for 24-48 hours after completion dependent on climatic conditions.
- It is advisable to apply a primer that is tinted to the required finish colour before the application of ROCKCOTE Sandcote HYDRATECH, if a coloured topcoat will not be used.

Technical Data Sheet

ROCKCOTE SANDCOTE HYDRATECH

Printed: March 21, 2018	Effective From	Effective To
Status at time of print: Active	21 Mar, 2018	

Precautions and Limitations

- Check colour before use.
- Ensure same batch numbers are used on a single wall where possible.
- Should not be applied in temperatures below 5°C or above 35°C.
- Not suitable for areas of continual damp or areas submerged in water.

Transport and Storage

- Store in a cool dark place.
- Keep pail sealed.
- Do not stack over 3 high.

Disposal

- Spilt Material must be absorbed with sand/sawdust and lifted for proper disposal
- Product must not be allowed to run into drains or open bodies of water
- Residual small amounts of leftover paint on brushes and rollers should be wiped on to an old newspaper and allowed to dry, rather than being washed down the sink. Dispose of in accordance with local council regulations
- Suitable for disposal through the RA Industries Reclaimer Portable Paint Wash Recycling System

Safety Data

Refer to ROCKCOTE Sandcote HYDRATECH SDS

Disclaimer

ROCKCOTE Enterprises Pty Ltd will not accept responsibility for any misuse of this product or if not applied by a skilled and experienced applicator and in accordance with our technical specifications. Due to our policy of continuing product improvement, ROCKCOTE Enterprises Pty Ltd reserves the right to change these specifications without further notice. Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and compensation for any other reasonably foreseeable loss or damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure.